

Table 1-8 (continued)
WT Shapes
Dimensions

Shape	Area, <i>A</i>	Depth, <i>d</i>	Stem			Flange			Distance		
			Thickness, <i>t_w</i>	$\frac{t_w}{2}$	Area	Width, <i>b_f</i>	Thickness, <i>t_f</i>	<i>k</i>	Workable Gage		
									in. ²	in.	
in. ²	in.	in.	in.	in.	in. ²	in.	in.	in.	in.	in.	in.
WT7×19 ^c	5.58	7.05	7	0.310	5/16	3/16	2.19	6.77	6 3/4	0.515	1/2
×17 ^c	5.00	6.99	7	0.285	5/16	3/16	1.99	6.75	6 3/4	0.455	7/16
×15 ^c	4.42	6.92	6 7/8	0.270	1/4	1/8	1.87	6.73	6 3/4	0.385	3/8
WT7×13 ^c	3.85	6.96	7	0.255	1/4	1/8	1.77	5.03	5	0.420	7/16
×11 ^{c,v}	3.25	6.87	6 7/8	0.230	1/4	1/8	1.58	5.00	5	0.335	5/16
WT6×168 ^h	49.4	8.41	8 3/8	1.78	1 3/4	7/8	14.9	13.4	13 3/8	2.96	2 15/16
×152.5 ^h	44.8	8.16	8 1/8	1.63	1 5/8	13/16	13.3	13.2	13 1/4	2.71	2 11/16
×139.5 ^h	41.0	7.93	7 7/8	1.53	1 1/2	3/4	12.1	13.1	13 1/8	2.47	2 1/2
×126 ^h	37.0	7.71	7 3/4	1.40	1 3/8	11/16	10.7	13.0	13	2.25	2 1/4
×115 ^h	33.9	7.53	7 1/2	1.29	1 5/16	11/16	9.67	12.9	12 7/8	2.07	2 1/16
×105	30.9	7.36	7 3/8	1.18	1 9/16	5/8	8.68	12.8	12 3/4	1.90	1 7/8
×95	27.9	7.19	7 1/4	1.06	1 1/16	9/16	7.62	12.7	12 5/8	1.74	1 3/4
×85	25.0	7.02	7	0.960	15/16	1/2	6.73	12.6	12 5/8	1.56	1 9/16
×76	22.4	6.86	6 7/8	0.870	7/8	7/16	5.96	12.5	12 1/2	1.40	1 3/8
×68	20.0	6.71	6 3/4	0.790	13/16	7/16	5.30	12.4	12 3/8	1.25	1 1/4
×60	17.6	6.56	6 1/2	0.710	11/16	3/8	4.66	12.3	12 3/8	1.11	1 1/8
×53	15.6	6.45	6 1/2	0.610	5/8	5/16	3.93	12.2	12 1/4	0.990	1
×48	14.1	6.36	6 3/8	0.550	9/16	5/16	3.50	12.2	12 1/8	0.900	7/8
×43.5	12.8	6.27	6 1/4	0.515	1/2	1/4	3.23	12.1	12 1/8	0.810	13/16
×39.5	11.6	6.19	6 1/4	0.470	1/2	1/4	2.91	12.1	12 1/8	0.735	3/4
×36	10.6	6.13	6 1/8	0.430	7/16	1/4	2.63	12.0	12	0.670	11/16
×32.5 ^f	9.54	6.06	6	0.390	3/8	3/16	2.36	12.0	12	0.605	5/8
WT6×29	8.52	6.10	6 1/8	0.360	3/8	3/16	2.19	10.0	10	0.640	5/8
×26.5	7.78	6.03	6	0.345	3/8	3/16	2.08	10.0	10	0.575	9/16
WT6×25	7.30	6.10	6 1/8	0.370	3/8	3/16	2.26	8.08	8 1/8	0.640	5/8
×22.5	6.56	6.03	6	0.335	5/16	3/16	2.02	8.05	8	0.575	9/16
×20 ^c	5.84	5.97	6	0.295	5/16	3/16	1.76	8.01	8	0.515	1/2
WT6×17.5 ^c	5.17	6.25	6 1/4	0.300	5/16	3/16	1.88	6.56	6 1/2	0.520	1/2
×15 ^c	4.40	6.17	6 1/8	0.260	1/4	1/8	1.60	6.52	6 1/2	0.440	7/16
×13 ^c	3.82	6.11	6 1/8	0.230	1/4	1/8	1.41	6.49	6 1/2	0.380	3/8

^c Shape is slender for compression with $F_y = 50$ ksi.

^f Shape exceeds compact limit for flexure with $F_y = 50$ ksi.

^g The actual size, combination, and orientation of fastener components should be compared with the geometry of the cross-section to ensure compatibility.

^h Flange thickness greater than 2 in. Special requirements may apply per Specification Section A3.1c.

^v Shear strength controlled by buckling effects ($C_v < 1.0$) with $F_y = 50$ ksi.

Related to Example 4-1 page 47

Table 1-8 (continued)
WT Shapes
Properties



Nominal Wt.	Compact Section Criteria	Axis X-X						Axis Y-Y						Q_s	Torsional Properties	
		b_f	h	I	S	r	\bar{y}	Z	y_p	I	S	r	Z	$F_y = 50$ ksi	J	C_w
		$2t_f$	t_w	in. ⁴	in. ³	in.	in.	in. ³	in.	in. ⁴	in. ³	in.	in. ³	in. ⁴	in. ⁶	
19	6.57	22.7	23.3	4.22	2.04	1.54	7.45	0.412	13.3	3.94	1.55	6.07	0.758	0.398	0.554	
17	7.41	24.5	20.9	3.83	2.04	1.53	6.74	0.371	11.6	3.45	1.53	5.32	0.668	0.284	0.400	
15	8.74	25.6	19.0	3.55	2.07	1.58	6.25	0.329	9.79	2.91	1.49	4.49	0.609	0.190	0.287	
13	5.98	27.3	17.3	3.31	2.12	1.72	5.89	0.383	4.45	1.77	1.08	2.76	0.538	0.179	0.207	
11	7.46	29.9	14.8	2.91	2.14	1.76	5.20	0.325	3.50	1.40	1.04	2.19	0.448	0.104	0.134	
168	2.26	4.74	190	31.2	1.96	2.31	68.4	1.84	593	88.6	3.47	137	1.00	120	481	
152.5	2.45	5.02	162	27.0	1.90	2.16	59.1	1.69	525	79.3	3.42	122	1.00	92.0	356	
139.5	2.66	5.18	141	24.1	1.86	2.05	51.9	1.56	469	71.3	3.38	110	1.00	70.9	267	
126	2.89	5.52	121	20.9	1.81	1.92	44.8	1.42	414	63.6	3.34	97.9	1.00	53.5	195	
115	3.11	5.86	106	18.5	1.77	1.82	39.4	1.31	371	57.5	3.31	88.4	1.00	41.6	148	
105	3.37	6.23	92.1	16.4	1.73	1.72	34.5	1.21	332	51.9	3.28	79.7	1.00	32.1	112	
95	3.65	6.78	79.0	14.2	1.68	1.62	29.8	1.10	295	46.5	3.25	71.2	1.00	24.3	82.1	
85	4.03	7.31	67.8	12.3	1.65	1.52	25.6	0.994	259	41.2	3.22	62.9	1.00	17.7	58.3	
76	4.46	7.88	58.5	10.8	1.62	1.43	22.0	0.896	227	36.4	3.19	55.6	1.00	12.8	41.3	
68	4.96	8.49	50.6	9.46	1.59	1.35	19.0	0.805	199	32.1	3.16	48.9	1.00	9.21	28.9	
60	5.57	9.24	43.4	8.22	1.57	1.28	16.2	0.716	172	28.0	3.13	42.7	1.00	6.42	19.7	
53	6.17	10.6	36.3	6.92	1.53	1.19	13.6	0.637	151	24.7	3.11	37.5	1.00	4.55	13.6	
48	6.76	11.6	32.0	6.12	1.51	1.13	11.9	0.580	135	22.2	3.09	33.7	1.00	3.42	10.1	
43.5	7.48	12.2	28.9	5.60	1.50	1.10	10.7	0.527	120	19.9	3.07	30.2	1.00	2.54	7.34	
39.5	8.22	13.2	25.8	5.03	1.49	1.06	9.49	0.480	108	17.9	3.05	27.1	1.00	1.91	5.43	
36	8.99	14.2	23.2	4.54	1.48	1.02	8.48	0.439	97.5	16.2	3.04	24.6	1.00	1.46	4.07	
32.5	9.92	15.5	20.6	4.06	1.47	0.985	7.50	0.398	87.2	14.5	3.02	22.0	1.00	1.09	2.97	
29	7.82	16.9	19.1	3.76	1.50	1.03	6.97	0.426	53.5	10.7	2.51	16.2	1.00	1.05	2.08	
26.5	8.69	17.5	17.7	3.54	1.51	1.02	6.46	0.389	47.9	9.58	2.48	14.5	1.00	0.788	1.53	
25	6.31	16.5	18.7	3.79	1.60	1.17	6.88	0.452	28.2	6.97	1.96	10.6	1.00	0.855	1.23	
22.5	7.00	18.0	16.6	3.39	1.59	1.13	6.10	0.406	25.0	6.21	1.95	9.47	0.996	0.627	0.885	
20	7.77	20.2	14.4	2.95	1.57	1.09	5.28	0.365	22.0	5.50	1.94	8.38	0.885	0.452	0.620	
17.5	6.31	20.8	16.0	3.23	1.76	1.30	5.71	0.394	12.2	3.73	1.54	5.73	0.855	0.369	0.437	
15	7.41	23.7	13.5	2.75	1.75	1.77	4.83	0.337	10.2	3.12	1.52	4.78	0.708	0.228	0.267	
13	8.54	26.6	11.7	2.40	1.75	1.25	4.20	0.295	8.66	2.67	1.51	4.08	0.567	0.150	0.174	




Table 1-8 (continued)
WT Shapes
Dimensions

Shape	Area, <i>A</i>	Depth, <i>d</i>	Stem			Flange			Distance					
			Thickness, <i>t_w</i>		Area	Width, <i>b_f</i>		Thickness, <i>t_f</i>	<i>k</i>	Workable Gage				
			in. ²	in.		in.	in. ²	in.	in.	in.				
WT6x11 ^c	3.24	6.16	6 1/8	0.260	1/4	1/8	1.60	4.03	4	0.425	7/16	0.725	15/16	2 1/4 ^g
WT6x9.5 ^c	2.79	6.08	6 1/8	0.235	1/4	1/8	1.43	4.01	4	0.350	3/8	0.650	7/8	
WT6x8 ^c	2.36	6.00	6	0.220	1/4	1/8	1.32	3.99	4	0.265	1/4	0.565	13/16	
WT6x7.5 ^{c,v}	2.08	5.96	6	0.200	3/16	1/8	1.19	3.97	4	0.225	1/4	0.525	3/4	↓
WT5x56	16.5	5.68	5 5/8	0.755	3/4	3/8	4.29	10.4	10 ³ /8	1.25	1 1/4	1.75	11 ⁵ /16	5 1/2
WT5x50	14.7	5.55	5 1/2	0.680	1 1/16	3/8	3.77	10.3	10 ³ /8	1.12	1 1/8	1.62	11 ³ /16	
WT5x44	12.9	5.42	5 5/8	0.605	5/8	5/16	3.28	10.3	10 ¹ /4	0.990	1	1.49	11 ¹¹ /16	
WT5x38.5	11.3	5.30	5 1/4	0.530	1/2	1/4	2.81	10.2	10 ¹ /4	0.870	7/8	1.37	19/16	
WT5x34	9.99	5.20	5 1/4	0.470	1/2	1/4	2.44	10.1	10 ¹ /8	0.770	3/4	1.27	17/16	
WT5x30	8.82	5.11	5 1/8	0.420	7/16	1/4	2.15	10.1	10 ¹ /8	0.680	11/16	1.18	13/8	
WT5x27	7.91	5.05	5	0.370	3/8	3/16	1.87	10.0	10	0.615	5/8	1.12	15/16	
WT5x24.5	7.21	4.99	5	0.340	5/16	3/16	1.70	10.0	10	0.560	9/16	1.06	11/4	
WT5x22.5	6.63	5.05	5	0.350	3/8	3/16	1.77	8.02	8	0.620	5/8	1.12	15/16	
WT5x19.5	5.73	4.96	5	0.315	5/16	3/16	1.56	7.99	8	0.530	1/2	1.03	13/16	
WT5x16.5	4.85	4.87	4 7/8	0.290	5/16	3/16	1.41	7.96	8	0.435	7/16	0.935	11/8	↓
WT5x15	4.42	5.24	5 1/4	0.300	5/16	3/16	1.57	5.81	5 3/4	0.510	1/2	0.810	1 1/8	2 3/4 ^g
WT5x13 ^c	3.81	5.17	5 1/8	0.260	1/4	1/8	1.34	5.77	5 3/4	0.440	7/16	0.740	11/16	↓
WT5x11 ^c	3.24	5.09	5 1/8	0.240	1/4	1/8	1.22	5.75	5 3/4	0.360	3/8	0.660	15/16	↓
WT5x9.5 ^c	2.81	5.12	5 1/8	0.250	1/4	1/8	1.28	4.02	4	0.395	3/8	0.695	15/16	2 1/4 ^g
WT5x8.5 ^c	2.50	5.06	5	0.240	1/4	1/8	1.21	4.01	4	0.330	5/16	0.630	7/8	
WT5x7.5 ^c	2.21	5.00	5	0.230	1/4	1/8	1.15	4.00	4	0.270	1/4	0.570	13/16	
WT5x6 ^{c,f}	1.77	4.94	4 7/8	0.190	3/16	1/8	0.938	3.96	4	0.210	3/16	0.510	3/4	↓
WT4x33.5	9.84	4.50	4 1/2	0.570	9/16	5/16	2.57	8.28	8 1/4	0.935	15/16	1.33	15/8	5 1/2
WT4x29	8.54	4.38	4 9/8	0.510	1/2	1/4	2.23	8.22	8 1/4	0.810	13/16	1.20	1 1/2	
WT4x24	7.05	4.25	4 1/4	0.400	3/8	3/16	1.70	8.11	8 1/8	0.685	11/16	1.08	13/8	
WT4x20	5.87	4.13	4 1/8	0.360	3/8	3/16	1.49	8.07	8 1/8	0.560	9/16	0.954	1 1/4	
WT4x17.5	5.14	4.06	4	0.310	5/16	3/16	1.26	8.02	8	0.495	1/2	0.889	13/16	
WT4x15.5 ^f	4.56	4.00	4	0.285	5/16	3/16	1.14	8.00	8	0.435	7/16	0.829	1 1/8	↓
WT4x14	4.12	4.03	4	0.285	5/16	3/16	1.15	6.54	6 1/2	0.465	7/16	0.859	15/16	3 1/2
WT4x12	3.54	3.97	4	0.245	1/4	1/8	0.971	6.50	6 1/2	0.400	3/8	0.794	7/8	3 1/2

^c Shape is slender for compression with $F_y = 50$ ksi.

^f Shape exceeds compact limit for flexure with $F_y = 50$ ksi.

^g The actual size, combination, and orientation of fastener components should be compared with the geometry of the cross-section to ensure compatibility.

^v Shear strength controlled by buckling effects ($C_v < 1.0$) with $F_y = 50$ ksi.

Table 1-8 (continued)
WT Shapes
Properties



Nominal Wt.	Compact Section Criteria		Axis X-X						Axis Y-Y						Q_s	Torsional Properties	
	b_f	h	I	S	r	\bar{y}	Z	y_p	I	S	r	Z	$F_y = 50$ ksi	J	C_w		
														$in.^4$	$in.^6$		
11	4.74	23.7	11.7	2.59	1.90	1.63	4.63	0.402	2.33	1.15	0.847	1.83	0.711	0.146	0.137		
9.5	5.72	25.9	10.1	2.28	1.90	1.65	4.11	0.348	1.88	0.939	0.821	1.49	0.598	0.0899	0.0934		
8	7.53	27.3	8.70	2.04	1.92	1.74	3.72	0.639	1.41	0.706	0.773	1.13	0.539	0.0511	0.0678		
7	8.82	29.8	7.67	1.83	1.92	1.76	3.32	0.760	1.18	0.593	0.753	0.947	0.451	0.0350	0.0493		
56	4.17	7.52	28.6	6.40	1.32	1.21	13.4	0.791	118	22.6	2.67	34.6	1.00	7.50	16.9		
50	4.62	8.16	24.5	5.56	1.29	1.13	11.4	0.711	103	20.0	2.65	30.5	1.00	5.41	11.9		
44	5.18	8.96	20.8	4.77	1.27	1.06	9.65	0.631	89.3	17.4	2.63	26.5	1.00	3.75	8.02		
38.5	5.86	10.0	17.4	4.05	1.24	0.990	8.06	0.555	76.8	15.1	2.60	22.9	1.00	2.55	5.31		
34	6.58	11.1	14.9	3.49	1.22	0.932	6.85	0.493	66.7	13.2	2.58	20.0	1.00	1.78	3.62		
30	7.41	12.2	12.9	3.04	1.21	0.884	5.87	0.438	58.1	11.5	2.57	17.5	1.00	1.23	2.46		
27	8.15	13.6	11.1	2.64	1.19	0.836	5.05	0.395	51.7	10.3	2.56	15.6	1.00	0.909	1.78		
24.5	8.93	14.7	10.0	2.39	1.18	0.807	4.52	0.361	46.7	9.34	2.54	14.1	1.00	0.693	1.33		
22.5	6.47	14.4	10.2	2.47	1.24	0.907	4.65	0.413	26.7	6.65	2.01	10.1	1.00	0.753	0.981		
19.5	7.53	15.7	8.84	2.16	1.24	0.876	3.99	0.359	22.5	5.64	1.98	8.57	1.00	0.487	0.616		
16.5	9.15	16.8	7.71	1.93	1.26	0.869	3.48	0.305	18.3	4.60	1.94	7.00	1.00	0.291	0.356		
15	5.70	17.5	9.28	2.24	1.45	1.10	4.01	0.380	8.35	2.87	1.37	4.41	1.00	0.310	0.273		
13	6.56	19.9	7.86	1.91	1.44	1.06	3.39	0.330	7.05	2.44	1.36	3.75	0.904	0.201	0.173		
11	7.99	21.2	6.88	1.72	1.46	1.07	3.02	0.282	5.71	1.99	1.33	3.05	0.837	0.119	0.107		
9.5	5.09	20.5	6.68	1.74	1.54	1.28	3.10	0.349	2.15	1.07	0.874	1.67	0.873	0.116	0.0796		
8.5	6.08	21.1	6.06	1.62	1.56	1.32	2.90	0.311	1.78	0.887	0.844	1.40	0.843	0.0776	0.0610		
7.5	7.41	21.7	5.45	1.50	1.57	1.37	2.71	0.305	1.45	0.723	0.810	1.15	0.810	0.0518	0.0475		
6	9.43	26.0	4.35	1.22	1.57	1.36	2.20	0.322	1.09	0.551	0.785	0.869	0.593	0.0272	0.0255		
33.5	4.43	7.89	10.9	3.05	1.05	0.936	6.29	0.594	44.3	10.7	2.12	16.3	1.00	2.51	3.56		
29	5.07	8.58	9.12	2.61	1.03	0.874	5.25	0.520	37.5	9.13	2.10	13.9	1.00	1.66	2.28		
24	5.92	10.6	6.85	1.97	0.986	0.777	3.94	0.435	30.5	7.51	2.08	11.4	1.00	0.977	1.30		
20	7.21	11.5	5.73	1.69	0.988	0.735	3.25	0.364	24.5	6.08	2.04	9.24	1.00	0.558	0.715		
17.5	8.10	13.1	4.82	1.43	0.968	0.688	2.71	0.321	21.3	5.31	2.03	8.05	1.00	0.384	0.480		
15.5																	